I claim:

- 1. A distillate fuel composition having improved stability and low temperature flow and filterability comprising a major portion of a distillate fuel and 100 to 5000 ppm of an additive composition comprising:
- (a) an olefin/vinyl carboxylate polymer selected from the group consisting of ethylene/vinyl acetate copolymers; ethylene/vinyl acetate/isobutylene terpolymers and mixtures thereof;
- (b) a first polyimide corresponding to the general formula:

$$\begin{array}{c|c} R_1 \\ | \\ CH_2 - CH - CH - CH \\ | \\ | \\ H \end{array}$$

where  $R_1$  is an alkyl group with an average carbon number of 22 to 26 carbon atoms and  $n_1$  is from about 1.5 to 8; and

(c) a second polyimide corresponding to the general formula

$$\begin{array}{c|c} R_2 \\ | \\ CH_2 - CH - CH - CH \\ O & | \\ I \\ H \end{array}$$

where  $R_2$  is an alkyl group with an average carbon number greater than 30 and  $n_2$  is from about 1.5 to 8.

2. The distillate fuel composition of Claim 1 wherein the weight ratio of olefin/vinyl carboxylate polymer to the combined weight of said first and second polyimides is from 4:1 to 1:4.

15 **88-1064A** 

- 3. The distillate fuel composition of Claim 2 wherein the weight ratio of said first polyimide to said second polyimide is from 1:5 to 5:1.
- 4. The distillate fuel composition of Claim 1 wherein the olefin/vinyl carboxylate polymer has a Brookfield viscosity of 100 to 300 centipoise at 140°C and vinyl acetate content of 25 to 55 weight percent.
- 5. The distillate fuel composition of Claim 4 wherein the vinyl acetate content of the olefin/vinyl carboxylate polymer is from 25 to 45 weight percent.
- 6. The distillate fuel composition of Claim 4 wherein the Brookfield viscosity of the olefin/vinyl carboxylate polymer is 100 to 200 centipoise at 140°C.
- 7. The distillate fuel composition of Claim 1 wherein  $R_1$  of the first polyimide is comprised of at least 60 percent  $C_{22-26}$  alkyl substituents,  $R_2$  of the second polyimide is comprised of at least 60 percent  $C_{33-36}$  alkyl substituents and the weight ratio of the first polyimide to second polyimide is from 1:2.5 to 2.5:1.
- 8. The distillate fuel composition of Claim 7 wherein the first polyimide has a number average molecular weight from 600 to 8000 and weight average molecular weight from 1500 to 15000.
- 9. The distillate fuel composition of Claim 7 wherein the second polyimide has a number average molecular weight from 650 to 9500 and weight average molecular weight from 2000 to 21000.
- 10. The distillate fuel composition of Claim 1 containing from 100 to 3000ppm of the additive composition.
- 11. The distillate fuel composition of Claim 1 wherein said distillate fuel is a hard-to-treat fuel.
- 12. A fuel additive composition for improving the low temperature flow and filterability of distillate fuels comprising:

- (a) an olefin/vinyl carboxylate polymer selected from the group consisting of ethylene/vinyl acetate copolymers; ethylene/vinyl acetate/isobutylene terpolymers and mixtures thereof;
- (b) a first polyimide corresponding to the general formula:

$$\begin{array}{c|c} R_1 \\ | \\ CH_2 - CH - CH - CH \\ | \\ O \end{array}$$

where  $R_1$  is an alkyl group with an average carbon number of 22 to 26 carbon atoms and  $n_1$  is from about 1.5 to 8; and

(c) a second polyimide corresponding to the general formula

$$\begin{array}{c|c}
 & R_2 \\
 & | \\
 & CH_2 - CH - CH - CH - CH \\
 & O & | \\
 & H & \\
\end{array}$$

where R<sub>2</sub> is an alkyl group with an average carbon number greater than 30 and n<sub>2</sub> is from about 1.5 to 8; said first polyimide and said second polyimide present at a weight ratio of 1:5 to 5:1 and the weight ratio of olefin/vinyl carboxylate polymer to the combined weight of said first and second polyimides ranging from 4:1 to 1:4.

13. The fuel additive of Claim 12 wherein the olefin/vinyl carboxylate polymer has a Brookfield viscosity of 100 to 300 centipoise at 140°C and vinyl acetate content of 25 to 55 weight percent.

- 14. The fuel additive of Claim 13 wherein the Brookfield viscosity of the olefin/vinyl carboxylate polymer is 100 to 200 centipoise at 140°C and the vinyl acetate content is from 25 to 45 percent.
- 15. The fuel additive of Claim 12 wherein  $R_1$  of the first polyimide is comprised of at least 60 percent  $C_{22-26}$  alkyl substituents,  $R_2$  of the second polyimide is comprised of at least 60 percent  $C_{33-36}$  alkyl substituents and the weight ratio of the first polyimide to second polyimide is from 1:2.5 to 2.5:1.
- 16. The fuel additive of Claim 15 wherein  $R_1$  of the first polyimide is comprised of at least 70 percent  $C_{22-26}$  alkyl substituents.
- 17. The fuel additive of Claim 16 wherein the first polyimide has a number average molecular weight from 600 to 8000 and weight average molecular weight from 1500 to 15000.
- 18. The fuel additive of Claim 15 wherein  $R_2$  of the second polyimide is comprised of at least 70 percent  $C_{30-36}$  alkyl substituents.
- 19. The fuel additive of Claim 18 wherein the second polyimide has a number average molecular weight from 650 to 9500 and weight average molecular weight from 2000 to 21000.
- 20. The fuel additive of Claim 1 wherein the weight ratio of olefin/vinyl carboxylate polymer to the combined weight of the first and second polyimides is from 2:1 to 1:2.